

MoldWiz® PLASTICS RESEARCH LABORATORIES. INC. MOLD RELEASES & PROCESS ADDITIVES

Mailing: Box 77 0855 Woodside, NY 11377 USA Shipping: 58-20 Broadway, Woodside, NY 11377 USA Phone: 718-672-8300 • Fax: 718-565-7447 E-mail: info @axelplastics.com

www.axelplastics.com

INT-38F

Technical Data Sheet

Process Aid Additive

Product Description

A process aid additive that Improves resin flow/fill, dispersion of other resin (reinforcements, fillers, and pigments), shortens cycle times, reduces temperatures and pressures of molding machines, and reduces or eliminates weld/knit lines.

Eliminates the need for an external mold release agent. An effective addition of this process aid additive will not have any adverse effect on physical properties or secondary operations such as decorating, printing, bonding, or plating.

Composition

Proprietary synergistic blend of organic fatty acids, esters and glycerides.

Handling

Keep container closed when not in use.

Uses

Nylon, Engineering Thermoplastics, PET, PBT Copolymers

Typical Properties

Effective Ingredients:	100%
Solids:	100%
Color:	Off-white
Dropping Point:	139°F/59.2°C
Flash Point:	Not Available
Shelf life	Minimum of one year
Availability:	Powder or Pellet form

Instructions for Use

For best results, laboratory tests or pre-production trials should determine the optimum addition level. MoldWiz® process aid additives are effective within a range of 1 to 10 parts per 1000 resin excluding reinforcements, pigments and fillers. A high amount of filler may require a higher percentage of process aid additive than the indicated maximum. Always start an evaluation at 5 parts per 1000 (0.5%). The process aid additive may increase the MFI. Reduce the level of additive or reduce the process temperature to raise the resin viscosity and to eliminate screw slippage.

Mixing: Dry blend the process aid additive by tumbling or use an additive dispenser to meter directly into the resin stream. Process aid additives may be compounded into the resin to make a masterbatch.

MoldWiz® is a registered trademark of Axel Plastics Research Laboratories.

This information is supplied for technically skilled professionals working at their own risk. AXEL believes the information to be accurate, although the Company assumes no liability in the validity of this information for any specific process or application. Moreover, AXEL will assume no liability from any direct and/or consequential damages of any kind that may arise from the use or non use of AXEL products or information supplied by the Company or its appointed representatives.

130626